

(12) **United States Patent**
Zeng et al.

(10) **Patent No.:** **US 9,224,855 B2**
(45) **Date of Patent:** **Dec. 29, 2015**

(54) **TRENCH GATED POWER DEVICE WITH MULTIPLE TRENCH WIDTH AND ITS FABRICATION PROCESS**

H01L 29/10 (2006.01)
H01L 29/40 (2006.01)
H01L 29/06 (2006.01)
H01L 29/08 (2006.01)

(71) Applicant: **MaxPower Semiconductor, Inc.**, Santa Clara, CA (US)

(52) **U.S. Cl.**
CPC **H01L 29/7813** (2013.01); **H01L 29/1095** (2013.01); **H01L 29/407** (2013.01); **H01L 29/41766** (2013.01); **H01L 29/4236** (2013.01); **H01L 29/66719** (2013.01); **H01L 29/66727** (2013.01); **H01L 29/66734** (2013.01); **H01L 29/0623** (2013.01); **H01L 29/0634** (2013.01); **H01L 29/0878** (2013.01); **H01L 29/404** (2013.01); **H01L 29/42368** (2013.01)

(72) Inventors: **Jun Zeng**, Torrance, CA (US);
Mohamed N. Darwish, Campbell, CA (US)

(73) Assignee: **MaxPower Semiconductor Inc.**, San Jose, CA (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 58 days.

(58) **Field of Classification Search**
CPC H01L 29/0623; H01L 29/0634; H01L 29/0878; H01L 29/7813; H01L 29/404; H01L 29/407; H01L 29/41766; H01L 29/4236; H01L 29/42368
See application file for complete search history.

(21) Appl. No.: **14/168,286**

(22) Filed: **Jan. 30, 2014**

(56) **References Cited**

(65) **Prior Publication Data**

US 2014/0239386 A1 Aug. 28, 2014

U.S. PATENT DOCUMENTS

7,598,143 B2 * 10/2009 Zundel et al. 438/270
8,420,483 B2 * 4/2013 Darwish 438/270

Related U.S. Application Data

* cited by examiner

(63) Continuation of application No. 13/525,908, filed on Jun. 18, 2012, now Pat. No. 8,680,607.

Primary Examiner — Michael Shingleton

(60) Provisional application No. 61/498,753, filed on Jun. 20, 2011.


(74) *Attorney, Agent, or Firm* — Robert O. Groover, III; Gwendolyn S. S. Groover; Groover & Associates PLLC

(51) **Int. Cl.**
H01L 29/49 (2006.01)
H01L 29/78 (2006.01)
H01L 29/417 (2006.01)
H01L 29/423 (2006.01)
H01L 29/66 (2006.01)

(57) **ABSTRACT**

Power devices, and related process, where both gate and field plate trenches have multiple stepped widths, using self-aligned process steps.

9 Claims, 48 Drawing Sheets






Figure 2
Trench Hard Mask #1




Figure 1
- Grow Oxide/Deposit Nitride




Figure 4

- Pad Oxide (not shown for simplification)
- Form 1st SiN Spacer

Figure 3

- 1st Trench Etch




Figure 6

- Spacer Removal
- Sac Oxidation and Removal




Figure 5

- 2nd Trench Etch




Figure 7

- Pad Oxide (not shown for simplification)
- Form 2nd SiN Spacer




Figure 8
- 3rd Trench Etch




Figure 9

- Oxide fills the trench's bottom portion




Figure 10

- Spacer Removal
- Hard Mask Removal




Figure 11
 - BOX mask#2
 - BOX Oxide Removal




Figure 12
 - Pad Oxidation Removal
 - Gate Oxidation




Figure 13

- PolySi Fill and Etch Back




Figure 14

- Source Mask#3
- N+ Source Implant (As or P)




Figure 15
- Poly Mask#4
- Field Plate PolySi Recess




Figure 16
- P-well Implant (B)
- Anneal




Figure 18
- Oxide Self-Aligned Recess




Figure 17
- Contact Mask#5
- Contact Etch




Figure 20

- Metallization
- Metal Mask#6
- Metal Etch




Figure 19

- P+ Body Contact Implant
- Anneal




Figure 21




Figure 22: Device structure and doping profiles
from 2-dimensional simulation




Figure 23: Contact Misalignment




Figure 24. Potential contours at the device breakdown




Figure 25
- Grow Oxide/Deposit Nitride




Figure 26
Trench Hard Mask #1




Figure 28
- Pad Oxide
- Form 1st SiN Spacer




Figure 27
- 1st Trench Etch




Figure 29
- Local doping enhancement implant (Phos)
- 2nd Trench Etch

Figure 30
- Spacer Removal
- Sac Oxidation and Removal




Figure 31

- Pad Oxide (not shown for simplification)
- Form 2nd SiN Spacer

Figure 32

- 3rd Trench Etch
- Local doping enhancement implant (P or As)




Figure 33

- LOCOS oxidation to fill the bottom portion




Figure 34

- Spacer Removal
- Hard Mask Removal




Figure 35

- BOX mask#2
- BOX Oxide Removal
- Boron Implant




Figure 36

- Pad Oxide Removal
- Gate Oxidation




Figure 38

- Source Mask#3
- N+ Source Implant (As or P)




Figure 37

- PolySi Fill and Etch Back




Figure 39

- Poly Mask#4
- Field Plate PolySi Recess




Figure 40

- P-well Implant (B)
- Anneal




Figure 41
Contact Mask#5
- Contact Etch




Figure 42
- Oxide Self-Aligned Recess




Figure 44

- Metallization
- Metal Mask#6
- Metal Etch




Figure 43

- P+ Body Implant
- Anneal




Figure 45




Figure 46
- Self-aligned Contact Etch




Figure 47
- Self-aligned P+ Body Implant (B11/BF2)




Figure 48




Figure 49A




Figure 49B




Figure 50




Figure 51A




Figure 51B




Figure 52




Figure 53




Figure 54




Figure 55A




Figure 55B




Figure 56




Figure 57B
- Oxide Self-Aligned Recess




Figure 57 A
- Etch or CMP surface oxide
- Contact Mask#5
- Contact Etch




Figure 57D

- Metallization
- Metal Mask#6
- Metal Etch




Figure 57C

- P+ Body Implant
- Anneal




Figure 58A




Figure 58B




Figure 58C




Figure 58D




Figure 58E






Figure 58F






Figure 58J





Figure 58I



1

TRENCH GATED POWER DEVICE WITH MULTIPLE TRENCH WIDTH AND ITS FABRICATION PROCESS

CROSS-REFERENCE

Priority is claimed from U.S. patent application 61/498,753 filed 20 Jun. 2011, which is hereby incorporated by reference.

BACKGROUND

The present application relates to power semiconductor devices, and more particularly to trench-gated power transistors having vertical current flow, especially in an embedded-recessed-field-plate structure.

Note that the points discussed below may reflect the hindsight gained from the disclosed inventions, and are not necessarily admitted to be prior art.

BRIEF DESCRIPTION OF THE DRAWINGS

The disclosed inventions will be described with reference to the accompanying drawings, which show important sample embodiments and which are incorporated in the specification hereof by reference, wherein:

FIGS. 1-20 show successive steps in a first example of a manufacturing process which implements many disclosed innovations.

FIG. 21 shows an example of the device structure produced by the steps of FIGS. 1-20.

FIG. 22 shows the internal doping profiles in the structure of FIG. 21.

FIG. 23 shows results of a comparative simulation to check sensitivity to lithographic misalignment.

FIG. 24 shows potential contours at the onset of the device breakdown, in a device like that of FIG. 21.

FIGS. 25 to 44 show successive steps in a second example of a manufacturing process which implements many disclosed innovations.

FIG. 45 shows an example of the device structure produced by the steps of FIGS. 25-44.

FIG. 46, FIG. 47, and FIG. 48 show some intermediate points in a third, process example, as well as modified device structures.

FIG. 49A shows a different example of a device structure which provides another implementation of various innovative concepts.

FIG. 49B shows yet another variation on various of the disclosed innovative concepts.

FIG. 50 shows yet another variation on various of the disclosed innovative concepts.

FIG. 51A shows yet another variation on various of the disclosed innovative concepts.

FIG. 51B shows yet another variation on various of the disclosed innovative concepts.

FIG. 52 shows yet another variation on various of the disclosed innovative concepts.

FIG. 53 shows yet another variation on various of the disclosed innovative concepts.

FIG. 54 shows yet another variation on various of the disclosed innovative concepts.

FIG. 55A shows yet another variation on various of the disclosed innovative concepts.

FIG. 55B shows yet another variation on various of the disclosed innovative concepts.

2

FIG. 56 shows yet another variation on various of the disclosed innovative concepts.

FIGS. 57A, 57B, 57C, and 57D show various stages in yet another sample process flow.

FIG. 58A shows yet another variation on various of the disclosed innovative concepts.

FIG. 58B shows yet another variation on various of the disclosed innovative concepts.

FIG. 58C shows yet another variation on various of the disclosed innovative concepts.

FIG. 58D shows yet another variation on various of the disclosed innovative concepts.

FIG. 58E shows yet another variation on various of the disclosed innovative concepts.

FIG. 58F shows yet another variation on various of the disclosed innovative concepts.

FIG. 58G shows yet another variation on various of the disclosed innovative concepts.

FIG. 58H shows yet another variation on various of the disclosed innovative concepts.

FIG. 58I shows yet another variation on various of the disclosed innovative concepts.

FIG. 58J shows yet another variation on various of the disclosed innovative concepts.

FIG. 58K shows yet another variation on various of the disclosed innovative concepts.

DETAILED DESCRIPTION OF SAMPLE EMBODIMENTS

The numerous innovative teachings of the present application will be described with particular reference to presently preferred embodiments (by way of example, and not of limitation). The present application describes several inventions, and none of the statements below should be taken as limiting the claims generally.

The present application describes new structures for trench-gated power semiconductor devices, and new processes for fabricating these devices with self-aligned spacings. In general, the new devices employ multiple trench widths with a self-aligned feature to achieve low specific on-resistance and low gate charge. Various disclosed examples use trenches which (as seen in profile) have three distinct widths, at top, middle, and bottom portions.

Preferably gate and field-plate trenches are etched in the same process sequence, and therefore have the same physical profile. This also provides self-alignment between adjacent trenches of the two types.

The middle portion of the gate trench has generally vertical sidewalls, and includes an insulated gate electrode. The top portion of the gate trench will be wider than the middle portion, and does not have to have vertical sidewalls. The bottom portion of the gate trench is preferably narrower than the middle portion of the same trench. The bottom portion of the field-plate trench is preferably narrower than the middle portion of the same trench. The fabrication process steps of the preferred embodiment result in the same sidewall profile for gate and field-plate trenches (top, middle, and bottom portions). However, as discussed below, some variations of these relations are also contemplated and disclosed.

An example of a manufacturing process is described in FIGS. 1-20. As shown in FIG. 1, the starting material (in this example) is an epitaxial structure of n- silicon **101** over an n++ substrate **100**. An oxide and nitride composite layer **102/104** is used to form the trench hard mask.

FIG. 2 shows the partially fabricated structure after the hard mask **102/104** has been patterned to expose trench locations **210**.

A first trench etch is now performed, as shown in FIG. 3. This etch will control the width of the top portion of the three-part trenches which will ultimately be formed.

Next, as shown in FIG. 4, a dielectric layer (e.g. Si_3N_4 , or more generally SiN_x) is conformally deposited and anisotropically etched. This creates the "sidewall spacer" structures **410**.

An anisotropic etch of silicon, with selectivity to nitride, is now performed (as shown in FIG. 5).

The spacer **410** is removed, and a sacrificial oxide is grown on exposed silicon, and removed. This smoothes the contours, and results in the partially formed structure of FIG. 6. Since the initial nitride layer **104** is much thicker than sidewall spacers **410**, layer **104** will not be removed when sidewall spacers **410** are removed.

A thin "pad oxide" layer (not shown) is now grown, and another sequence of conformal deposition followed by anisotropic etch is performed to leave another sidewall spacer **710**. This results in the structure of FIG. 7.

Another silicon etch (selective to nitride) now results in the structure of FIG. 8.

With the pad oxide and silicon nitride stack **710** still in place, an oxidation is now performed to fill the bottom portions of the trenches. This results in the structure of FIG. 9. The top contour of the oxide **912** may vary in dependence on the duration of this oxidation.

After removal of the SiN spacer **710** and the remaining portions of hard mask **102/104**, the structure of FIG. 10 results.

This is now patterned (using photoresist **1105**) and etched to leave oxide in the bottom part of first trenches **1110**, while removing oxide from second trenches **1120**. This results in the structure of FIG. 11. Prior to this point all of the trenches have preferably been the same; after this point the structure of the first trenches **1110** (which will contain insulated trench gates) is different from that of the second trenches **1120** (which will contain field plates).

The photoresist is removed, and a thermal oxidation is taken place to grow a high quality gate oxide **1230** along trench sidewalls, as shown in FIG. 12.

A conductive material (preferably n-type polysilicon) is now deposited overall, and etched back to provide conductive plugs **1310** in all the trenches. This results in the structure of FIG. 13. Note that these plugs **1310** are deeper in the second trenches **1120** (where they extend down into the bottom portion of the trench) than in the first trenches **1110**.

A donor dopant (e.g. arsenic or phosphorus) is implanted into the wafer surface to form the n+ source region **1440** (FIG. 14). Note that the n+ source region **1440** has a non-uniform depth conforming to the depth profile of the top portion of the trenches: source region **1440** is shallower in the mesa areas, and becomes deeper near the trench sidewalls. This is preferably a masked implant, although the relevant mask does not appear in the small active device region shown.

As shown in FIG. 15, another photoresist mask **1505** is used to pattern an etch which etches back the polysilicon plugs **1310**, in second trench locations, to leave recessed field plates **1550**. (As discussed below, a variety of other process steps can be used to modify this structure if desired.)

After the photoresist **1505** is removed, a p-type dopant, such as Boron, is implanted into the silicon, and a high temperature annealing step is carried out, to form the P-well (body) region **1660** as shown by FIG. 16. Again, as can be seen, the P-well depth is not uniform and is deeper near the

trench sidewall due to the existence of the non-uniform implant surface. The deepest portion is located along the trench sidewall of the second trenches **1120**. This kind of P-well profile is desirable for improving the device breakdown and ruggedness characteristics, without degrading the on-resistance.

After deposition of an interlevel dielectric ("ILD") layer **1770** (such as BPSG and LTO), photoresist **1705** is patterned to remove the ILD **1770** and open up parts of the n+ source area **1440** (FIG. 17).

Subsequently, the contact silicon recess is produced in a self-aligned manner, by performing a selective etch to form a recess over the field plate **1550**. By using an oxide etch which stops on silicon, precise timing and process control is less necessary; this is an improvement over use of a silicon etch as usually done in the conventional trench MOSFET.

This self-aligned contact recess etch can be followed by a brief reoxidation (or conformal deposition), advantageously resulting in the structure of FIG. 18. Note that, since the top of field plate **1550** is well below the deepest part of source **1440**, a significant area **1860** of P-well **1660** is exposed at the sidewalls of second trenches **1120**.

The exposed area of P-well gives room to accommodate the P+ body contact region **1962**, and the area where metal makes ohmic contact to P+ region **1962**. This is shown in FIG. 19. The P+ body contact region **1962** in FIG. 19 is created by implanting acceptors (such as BF_2 and/or B^{11}) followed by a high temperature anneal step. The contact area of this P+ region **1962** can be adjusted by properly adjusting the depth of the self-aligned oxide recess during the etchback step of FIG. 15. Moreover, since the acceptor implant which forms P+ regions **1962** has a much smaller implant dose ($\sim 1\text{E}15/\text{cm}^2$) than the donor implant which forms n+ source regions **1440** ($\sim 1\text{E}16/\text{cm}^2$), the impact of the P+ implant on the n+ source will be completely compensated inside the n+ source region, leaving the P+ only formed in areas lacking the n+ source dopants, i.e. in the P-well exposed area **1860**.

After the source metallization, the n+ source and P+ body regions **1440** and **1660** will be shorted together by the top metal layer **2080** (FIG. 20).

With completion of backside grind and deposition of backside metal **2101**, the final device structure is produced as given in FIG. 21. Note that, although the structures inside the first and second trenches are different, the profiles of the two types of trenches are the same: each has a top portion **2110**, a middle portion **2120**, and a bottom portion **2130**. Note also that the middle portions have essentially vertical sidewalls. The bottom portions, in this example, have generally vertical sidewalls except at their bottom corners. Note also that the top portions have less depth than the middle portion. The bottom portions also preferably have less depth than the middle portions in this example, but this will be somewhat affected by the operating voltage specification of the device. The first trenches **1110** each include a gate electrode **2152**, which can be modified as described below. This gate electrode will normally be connected to a gate drive connection outside the plane of the device cross-section shown here. The second trenches **1120** each include a field plate **1550**, which can be connected (outside the plane of the device cross-section shown here) to source potential. Alternatively, the field plate electrode **1550** can be connected to a different fixed potential, or to a variable potential which is affected by gate voltage, or even (less preferably) left floating.

The drawings described above are sketches which show the expected spatial relationships resulting from the process flow as described. In addition, a two-dimensional process simulation has been run on the process flow described above. FIG.

22 shows the final device structure, and internal doping profiles, corresponding to the sequence of FIGS. 1-21.

In practice, an important measure of the manufacturability of a semiconductor process flow is its sensitivity to misalignments. To measure this with the above flow, the impact of contact misalignment on P+ body and n+ source has been simulated, and the results are presented in FIG. 23. This clearly shows that even with 70 nm misalignment, the P+ body and n+ source profile are very similar, and, more important, the misalignment has little impact on the channel doping profile (thanks to the self-aligned contact silicon recess and the non-uniform depth of the n+ source). In consequence, this misalignment has little impact on device electrical parameters including the threshold voltage V_{TH} and the specific on-resistance R_{SP} as well as the breakdown voltage BVDS.

Additionally, as mentioned in previous paragraph, the unique P-well profile helps to improve the breakdown characteristic of the device. This is clearly verified by the simulated potential contours at the onset of the device breakdown, as shown in FIG. 24. It can be seen that the deep portion of the P-well pushes much of the voltage drop down into the epitaxial layer, and limits the isopotential lines from extending into the channel region, thus leading to a reduction of the device leakage current.

The above simulations used the example of a 30V-rated device with a pitch of 1.4 micron. Actual device breakdown was found to occur at about 33 Volts. The on-state specific resistivity was found to be 8.77 mΩ·mm². These are good numbers for a low-voltage power device.

A further improvement of the devices and processes described above can be achieved by the forming the so-called charge balanced EPI layer of the device. This can be accomplished by introducing couple additional implants at different process points.

FIGS. 25 to 44 describe one sample implementation of this improvement. This process sequence is generally very similar to that of FIGS. 1-20, except as noted.

FIGS. 25, 26, 27, and 28 are generally identical to FIGS. 1-4.

FIG. 29 shows how, after the 2nd trench etch, donor atoms (e.g. phosphorus, arsenic, or a combination of the two) is introduced by implant to locally adjust the doping concentration inside the EPI layer at the first depth.

As shown in FIG. 30, this results in an enhanced donor concentration in regions 3001, above the rest of epitaxial layer 101.

FIG. 31 and FIG. 32 are generally similar to the corresponding figures in the first process flow, except that an additional N-type doping concentration enhancement at the 2nd depth is done after the 3rd trench etch, e.g. by phosphorous or arsenic implantation through the bottoms of the trenches.

After this process step, as shown in FIG. 33, the doping in region 3301 is highly enhanced, and this reduces the resistance of the drift region. (Region 3001 is omitted for simplicity in this drawing, since regions 3001 and 3301 are not sharply distinct.)

FIG. 34 shows further processing, which corresponds to that shown in FIG. 10 above.

The additional doping in region 3301, by itself, would tend to degrade the device breakdown voltage. In order to eliminate this negative impact, the P-type dopant Boron is implanted into the EPI in FIG. 35 after the removal of buried oxide ("BOX") layer 912. By properly choosing the implant doses, a charge balanced EPI layer can be formed and the device breakdown voltage will not decrease with the increased conductivity due to doping enhancement 3301.

Therefore, the improved device will have a lower on-resistance for a given breakdown voltage.

The implant step of FIG. 35 results in a p-type shield region 3602, as shown in FIG. 36. This provides the advantages just described.

The remaining process steps, successively shown in FIG. 37, FIG. 38, FIG. 39, FIG. 40, FIG. 41, FIG. 42, FIG. 43, and FIG. 44, are generally the same as those shown in FIGS. 13-20 and described above. The final device structure is depicted in FIG. 45.

In another class of alternative implementations, the contact self-aligned silicon etch is performed by employing the oxide-filled 1st trench as the mask, without using the additional photoresist mask. This is illustrated in FIG. 46. The space between the contact edge and the sidewall channel inside the 2nd trench can be adjusted by changing the width of the 1st trench. The implementation of this scheme is briefly demonstrated through FIG. 46, FIG. 47, and FIG. 48. In this sequence, a trench MOSFET with a thick BOX layer and an optimized P-well junction profile is used as the example. Note that the p+ region 4762, which makes ohmic contact from the p-well 1660 to the front metal, is formed differently from the p+ body contact region 1962 which is shown in FIG. 19 and following.

The concepts disclosed in this application are not limited to the examples discussed in the paragraphs above. They can be used for developing many different device structures such as the devices illustrated in FIG. 49A and following FIGS.

FIG. 49A shows a device structure which is generally somewhat similar to that of FIG. 45, except that the modified process steps of FIGS. 46-48 have been used.

FIG. 49B shows a device structure which is generally somewhat similar to that of FIG. 49A, except that in FIG. 49B there is not any oxide layer between source metal and field plate electrode (at the location shown). In FIG. 49B the source metal is in direct contact with the field plate electrode.

FIG. 50 shows a device structure which is generally somewhat similar to that of FIG. 21, except that a shield electrode 5002 is present below the gate electrode in the first trenches. This advantageously reduces gate-drain parasitic capacitance.

FIG. 51A shows a device structure which is generally somewhat similar to that of FIG. 21, except that a shield electrode 5102 is present below the gate electrode in the first trenches. The shield electrode is preferably connected to the source electrode at certain places in the device (not shown). This too advantageously reduces gate-drain parasitic capacitance.

FIG. 51B shows a device structure which is generally somewhat similar to that of FIG. 21, except that a shield electrode 5102 is present below the gate electrode in the first trenches, and the field plate has been split into an upper part 5151 and a lower part 5153.

FIG. 52 shows a device structure which is generally somewhat similar to that of FIG. 45, except that the gate electrode 5252 has a lower extension surrounded by thick insulation.

FIG. 53 shows a device structure which combines the modifications of FIGS. 51A and 52, and also includes a field plate electrode 5350 which has a lower extension surrounded by thick insulation.

FIG. 54 shows a device structure which is generally somewhat similar to that of FIG. 53, except that the modified process steps of FIGS. 46-48 have been used.

FIG. 55A and FIG. 55B show alternative implementations where the p-type region 3604 below the field plate has been replaced by near-intrinsic regions, of p-type and n-type respectively.

Another implementation of some of the disclosed inventions is shown in FIG. 56, where the source metal is planar to the silicon surface. In this example the interlevel dielectric portions 1770, which are visible in (e.g.) the examples of FIG. 17 and FIG. 45, are not present.

This structure provides a larger contact area to the source n+ region and results in reduced on-resistance. The process is slightly modified from the previously discussed flow as shown in FIGS. 57A-57D.

In FIG. 57A surface oxide is planarized/etched leaving a thin oxide layer (100 Å-300 Å) at the surface before applying the contact mask. After etching the contact opening (FIG. 57B) the remaining thin oxide layer at the surface is etched as shown in FIG. 57C. FIG. 57D shows the resulting structure after metallization.

Other examples of the planar source metal structures are shown in FIGS. 58A-58K. FIG. 58A shows an example of an implementation which is generally somewhat similar to that of FIG. 54, except that the shield electrodes 5102 are not used.

FIG. 58B shows an example of an implementation which is generally somewhat similar to that of FIG. 58A, except that shield electrodes 5002 are used, and p+ body contact regions 1962 are used rather than p+ body contact regions 4762.

FIG. 58C shows an example of an implementation which is generally somewhat similar to that of FIG. 58B, except that the shield electrodes 5102 are used instead of the shield electrodes 5002.

FIG. 58D shows an example of an implementation which is generally somewhat similar to that of FIG. 58C, except that, instead of shield electrodes 5102, the gate electrode 5252 is shaped to have a downward extension which is surrounded by thicker insulation.

FIG. 58E shows an example of an implementation which is generally somewhat similar to that of FIG. 58C, except that the field plate 5350 is shaped to have a downward extension which is surrounded by thicker insulation.

FIG. 58F shows an example of an implementation which is generally somewhat similar to that of FIG. 58E, except that p+ body contact regions 1962 are used rather than p+ body contact regions 4762.

FIG. 58G shows an example of an implementation which is generally somewhat similar to that of FIG. 52, except that p-type region 3602 has been replaced by a region 5802 of near-intrinsic p-type doping ("π").

FIG. 58H shows an example of an implementation which is generally somewhat similar to that of FIG. 52, except that p-type region 3602 has been replaced by a region 5804 of near-intrinsic n-type doping ("ν").

FIG. 58I shows an example of an implementation which is generally somewhat similar to that of FIG. 58E, except that an air gap 5805 is included below shield plates 5002.

FIG. 58J shows an example of an implementation which is generally somewhat similar to that of FIG. 58I, except for the absence of shield plates 5002.

FIG. 58K shows an example of an implementation which is generally somewhat similar to that of FIG. 58C, except that the field plate electrode is not insulated from the front metal 2090 in the locations shown.

According to some, but not necessarily all disclosed implementations, there is provided: A semiconductor device, comprising: a semiconductor mass; gate electrodes in first trenches in said semiconductor mass, and field plate electrodes in second trenches in said semiconductor mass; wherein said first trenches and said second trenches have substantially the same depth; wherein said first and said second trenches each have a top portion which is wider than a middle portion thereof which has substantially vertical side-

walls, and also a bottom portion which is narrower than said middle portion; a first-conductivity-type source region, in said semiconductor mass, near said first trenches, and a second-conductivity-type body region adjacent said first trenches, and a second-conductivity-type body contact region surrounding said second trenches.

According to some, but not necessarily all disclosed implementations, there is provided: A semiconductor device, comprising: a semiconductor mass; gate electrodes in first trenches in said semiconductor mass, and field plate electrodes in second trenches in said semiconductor mass; wherein said first trenches and said second trenches both extend into a first surface of said semiconductor mass, and all have substantially the same depth; wherein said first and said second trenches each have a top portion which is wider than a middle portion thereof which has substantially vertical side-walls, and also a bottom portion which is narrower than said middle portion; and wherein said gate electrodes, but not said field plate electrodes, are connected directly to receive a gate drive waveform; a first-conductivity-type source region, in said semiconductor mass, near said first trenches, and a second-conductivity-type body region adjacent said first trenches, and a second-conductivity-type body contact region surrounding and self-aligned to said second trenches; and a first-conductivity-type drain region at a second surface of said semiconductor mass; whereby, in the ON state, voltage applied to said gate electrode controls majority carrier emission from said source, to thereby allow current conduction between said source and said drain; and whereby said field plate electrodes affect isopotential contours, in the OFF state, to increase the breakdown voltage between said source and said drain.

According to some, but not necessarily all disclosed implementations, there is provided: A semiconductor device, comprising: a semiconductor mass; gate electrodes in first trenches in said semiconductor mass, and field plate electrodes in second trenches in said semiconductor mass; wherein said first trenches and said second trenches have substantially the same depth; wherein said first and said second trenches each have a top portion which is wider than a middle portion thereof which has substantially vertical side-walls, and also a bottom portion which is narrower than said middle portion; a first-conductivity-type source region, in said semiconductor mass, adjacent and self-aligned to said first trenches; a second-conductivity-type body region adjacent said first trenches; a second-conductivity-type body contact region surrounding and self-aligned to said second trenches; and modified regions, below and self-aligned to said second trenches, which have a smaller net concentration of second-conductivity-type dopants than said body region does.

According to some, but not necessarily all disclosed implementations, there is provided: A semiconductor device, comprising: a semiconductor mass; gate electrodes in first trenches in said semiconductor mass, and field plate electrodes in second trenches in said semiconductor mass; wherein said first trenches and said second trenches have substantially the same depth; wherein said first and said second trenches each have a top portion which is wider than a middle portion thereof which has substantially vertical side-walls, and also a bottom portion which is narrower than said middle portion; a first-conductivity-type source region, in said semiconductor mass, adjacent and self-aligned to said first trenches; a second-conductivity-type body region adjacent said first trenches; a second-conductivity-type body contact region surrounding and self-aligned to said second trenches; and modified regions, below and self-aligned to said

second trenches, which have a smaller net concentration of second-conductivity-type dopants than said body region does.

According to some, but not necessarily all disclosed implementations, there is provided: A semiconductor device, comprising: a semiconductor mass; gate electrodes, and shield electrodes beneath said gate electrodes, in first trenches in said semiconductor mass, and field plate electrodes in second trenches in said semiconductor mass; wherein said first trenches and said second trenches both extend into a first surface of said semiconductor mass, and all have substantially the same depth; wherein said first and said second trenches each have a top portion which is wider than a middle portion thereof which has substantially vertical sidewalls, and also a bottom portion which is narrower than said middle portion; and wherein said gate electrodes, but not said field plate electrodes, are connected directly to receive a gate drive waveform; a first-conductivity-type source region, in said semiconductor mass, near said first trenches, and a second-conductivity-type body region adjacent said first trenches, and a second-conductivity-type body contact region surrounding and self-aligned to said second trenches; and a first-conductivity-type drain region at a second surface of said semiconductor mass; whereby, in the ON state, voltage applied to said gate electrode controls majority carrier emission from said source, to thereby allow current conduction between said source and said drain; and whereby said field plate electrodes affect isopotential contours, in the OFF state, to increase the breakdown voltage between said source and said drain.

According to some, but not necessarily all disclosed implementations, there is provided: A method of fabricating a power semiconductor device, comprising: etching a plurality of trenches into a semiconductor mass, using at least two sidewall spacer operation to form individual ones of said trenches with a stepped width; providing a dielectric which fills lowermost portions of first ones of said trenches, but not second ones of said trenches; forming insulated gate electrodes in said first trenches, but not in said second trenches; forming a first-conductivity-type source region and a second-conductivity-type body region in proximity to said first trenches; forming second-conductivity-type body contact regions in said sc mass adjacent said second trenches; and electrically connecting said source, gate, and body contact regions to provide an operative active device.

According to some, but not necessarily all disclosed implementations, there is provided: Power devices, and related process, where both gate and field plate trenches have multiple stepped widths, using self-aligned process steps.

The disclosed innovations, in various alternative implementations, provide one or more of at least the following advantages. However, not all of these advantages result from every one of the innovations disclosed, and this list of advantages does not limit the various claimed inventions.

Higher breakdown voltage, for a given on-state current density;
Higher breakdown voltage;
Higher on-state current density;
Higher on-state current density for a given breakdown voltage;
Denser layout;
Simpler fabrication; and
Less process variation in the electrical characteristics of finished devices.

Modifications and Variations

As will be recognized by those skilled in the art, the innovative concepts described in the present application can be

modified and varied over a tremendous range of applications, and accordingly the scope of patented subject matter is not limited by any of the specific exemplary teachings given. It is intended to embrace all such alternatives, modifications and variations that fall within the spirit and broad scope of the appended claims.

All the above variants of the structure can be realized in stripe or cellular layout such as square, rectangular, hexagonal or circular layouts.

The disclosed inventions are also applicable to p-channel devices, with reversal of voltage, dopant, and permanent charge polarities.

Even though the embodiments above are for MOSFET structures, the various disclosed inventions are applicable to other devices such as Insulated Gate Bipolar Transistors (IGBTs), thyristors, and other devices that can block voltages.

For another example, the semiconductor material does not necessarily have to be silicon, as in the preferred embodiment. This can alternatively be SiGe or SiGeC or other Group IV semiconductor alloy.

It is understood that numerous combinations of the above embodiments are also possible.

None of the description in the present application should be read as implying that any particular element, step, or function is an essential element which must be included in the claim scope: THE SCOPE OF PATENTED SUBJECT MATTER IS DEFINED ONLY BY THE ALLOWED CLAIMS. Moreover, none of these claims are intended to invoke paragraph six of 35 USC section 112 unless the exact words "means for" are followed by a participle.

Additional general background, which helps to show variations and implementations, as well as some features which can be combined synergistically with the inventions claimed below, may be found in the following patent applications. All of these applications have at least some common ownership, copendency, and inventorship with the present application. All of these applications, and all of their priority applications, are hereby incorporated by reference:

published PCT application WO2012006261;
published PCT application WO2011133481;
published PCT application WO2011087994;
published PCT application WO2011035331;
published PCT application WO2011008717;
published PCT application WO2010120704;
published PCT application WO2010098742;
published US application US20080073707;
published US application US20080191307;
published US application US20080164516;
published US application US20080164518;
published US application US20080164520;
published US application US20080166845;
published US application US20090206924;
published US application US20090206913;
published US application US20090294892;
published US application US20090309156;
published US application US20100013552;
published US application US20100025726;
published US application US20100025763;
published US application US20100084704;
published US application US20100219462;
published US application US20100219468;
published US application US20100214016;
published US application US20100308400;
published US application US20100327344;
published US application US20110006361;
published US application US20110039384;
published US application US20110079843;

11

published US application US20110169103;
 published US application US20110193131;
 published US application US20110254088;
 published US application US20110220998;
 published US application US20110298043;
 published US application US20120098056;
 published US application US20120098055;
 published US application US20120043602;
 published US application US20120032258;
 published US application US20120098055;
 published US application US20120098056;
 unpublished U.S. application Ser. No. 12/369,385;
 unpublished U.S. application Ser. No. 12/720,856;
 unpublished U.S. application Ser. No. 12/835,636;
 unpublished U.S. application Ser. No. 12/939,154;
 unpublished U.S. application Ser. No. 13/212,044;
 unpublished U.S. application Ser. No. 13/418,615.

Applicants reserve the right to claim priority from these applications, directly or indirectly, and therethrough to even earlier applications, in all countries where such priority can be claimed.

Further background, and indications of variations which will be immediately understood by persons of ordinary skill in the art, can be found e.g. in B. Baliga, Modern Power Devices (1992); B. Baliga, Fundamentals of Power Semiconductor Devices (2008); and all of the annual proceedings of the ISPSD symposia; all of which are hereby incorporated by reference.

The claims as filed are intended to be as comprehensive as possible, and NO subject matter is intentionally relinquished, dedicated, or abandoned.

What is claimed is:

1. A semiconductor device, comprising:

a semiconductor mass;

gate electrodes, and shield electrodes beneath said gate electrodes, in first trenches in said semiconductor mass, and field plate electrodes in second trenches in said semiconductor mass; wherein said first trenches and said second trenches both extend into a first surface of said semiconductor mass, and all have substantially the same depth; wherein said first and said second trenches each have a top portion which is wider than a middle portion thereof which has substantially vertical sidewalls, and also a bottom portion which is narrower than said middle

12

portion; and wherein said gate electrodes, but not said field plate electrodes, are connected directly to receive a gate drive waveform;

a first-conductivity-type source region, in said semiconductor mass, near said first trenches, and a second-conductivity-type body region adjacent said first trenches, and a second-conductivity-type body contact region surrounding and self-aligned to said second trenches; and a first-conductivity-type drain region at a second surface of said semiconductor mass;

whereby, in the ON state, voltage applied to said gate electrode controls majority carrier emission from said source, to thereby allow current conduction between said source and said drain; and whereby said field plate electrodes affect isopotential contours, in the OFF state, to increase the breakdown voltage between said source and said drain.

2. The semiconductor device of claim 1, wherein said first conductivity type is n-type, and said second conductivity type is p-type.

3. The semiconductor device of claim 1, wherein said semiconductor mass consists essentially of silicon.

4. The semiconductor device of claim 1, wherein said gate electrodes are made of doped polysilicon.

5. The semiconductor device of claim 1, wherein said middle portion of each said trench has a greater vertical extent than said bottom portion thereof, and said bottom portion of each said trench has a greater vertical extent than said top portion thereof.

6. The semiconductor device of claim 1, wherein said gate electrode does not extend into said bottom portion of said first trench, and said field plate electrode does extend into said bottom portion of said second trench.

7. The semiconductor device of claim 1, wherein doping for said body region is provided by a well diffusion process.

8. The semiconductor device of claim 1, further comprising a first-conductivity-type drift region interposed between said body region and said drain region.

9. The semiconductor device of claim 1, further comprising a first-conductivity-type drift region interposed between said body region and said drain region, said drift region having an uppermost portion, adjacent said body region, which is more heavily doped than middle portions of said drift region which are generally halfway between said body region and said drain region.

* * * * *